


**AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**LISTING OF CLAIMS:**



Claims 1-58 (Canceled)

59. (Currently Amended) A process for the preparation of a low-viscosity (poly)isocyanate composition comprising at least one isocyanate dimer containing a uretidinedione unit and at least 1 weight % of at least one carbamate function, from starting isocyanate monomers in which the isocyanate groups are borne by  $sp^3$  carbon atoms, comprising the step of heating a starting reaction medium comprising said isocyanate monomers, in the absence of a dimerization catalyst, to a temperature of at least  $50^{\circ}\text{C}$  and of not more than  $200^{\circ}\text{C}$  for a period of not more than 24 hours, the reaction medium containing the starting monomers also containing a compound of general formula I:




in which R is a mono- or n-valent hydrocarbon group having from 1 to 30 carbon atoms, in which the hydrocarbon chain optionally is interrupted by one or more chalcogen atoms and optionally, bears 1 to 3 OH groups, and n is an integer ranging from 1 to 3, said composition optionally containing products derived from reaction of said compound of formula I with a compound bearing an aliphatic isocyanate function.

60. (Currently Amended) A process according to claim 59, comprising adding to the reaction medium containing the starting monomers a compound of general formula II and/or III below:




in which one or more of  $X_1$ ,  $X_2$  and  $X_3$  represents a group  $R'-(N=C=O)_p$  in which  $R'$  is an aliphatic group and  $p$  is an integer ranging from 0 to 5, the others representing, a group of formula




$R_1$  is a hydrocarbon group having 1 to 30 carbon atoms, in which the hydrocarbon chain optionally is interrupted by one or more chalcogen atoms and optionally, bears

1 to 3 OH groups, with the OH groups optionally substituted, with a group CONX<sub>1</sub>H, X<sub>1</sub> being as defined above, at least one of NX'<sub>1</sub>X''<sub>1</sub>, NX'<sub>2</sub>X''<sub>2</sub> and NX'<sub>3</sub>X''<sub>3</sub> represents the group,



the others representing a group NX<sub>1</sub>H or NX<sub>1</sub>-silyl and R<sub>2</sub> being a hydrocarbon group having 1 to 30 carbon atoms, in which the hydrocarbon chain optionally is interrupted by one or more chalcogen atoms and optionally, bears 1 to 3 OH groups, with the OH groups optionally substituted, with a group CONX<sub>1</sub>H, or




and n is an integer ranging from 1 to 3.

61. (Previously Presented) A process according to Claim 59, wherein R is a C<sub>1</sub>-C<sub>4</sub> alkyl group substituted with 1 to 3 OH groups.


62. (Previously Presented) A process according to Claim 60, wherein said compound of general formula I is selected from pentaerythritol or trimethylolpropane, and the compounds of general formulae II and III are selected from the corresponding pentaerythritol or trimethylolpropane derivatives of general formula II or III or both II and III wherein R<sub>1</sub> or R<sub>2</sub> or both R<sub>1</sub> and R<sub>2</sub> represents a group selected from CH<sub>2</sub>OH or CH<sub>3</sub>CH<sub>2</sub>.

Claims 63-65 (Canceled)


66. (Currently Amended) A composition comprising at least one compound of general formula X:



in which R' is an aliphatic group and p is an integer ranging from 0 to 5, and at least one compound of general formula II:




in which one or more of X<sub>1</sub>, X<sub>2</sub> and X<sub>3</sub> represents a group -R'(-N=C=O)<sub>p</sub> and the others represent, a group




and  $R_1$  is a hydrocarbon group having 1 to 30 carbon atoms, in which the hydrocarbon chain optionally is interrupted by one or more chalcogen atoms and optionally bears 1 to 3 OH group, with the OH groups optionally substituted with a group  $\text{CONX}_1\text{H}$  wherein  $X_1$  represents  $\text{R}'\text{---}(\text{N}=\text{C}=\text{O})_p$

and  $n$  is an integer from 1 to 3;

and/or at least one compound of general formula III:




in which at least one of  $\text{NX}'_1\text{X}''_1$ ,  $\text{NX}'_2\text{X}''_2$  and  $\text{NX}'_3\text{X}''_3$  represents the group,




the others representing a group  $\text{NX}_1\text{H}$  and

$R_2$  being a hydrocarbon group having 1 to 30 carbon atoms, in which the hydrocarbon chain optionally is interrupted by one or more chalcogen atoms and

optionally, bears 1 to 3 OH groups, with the OH groups optionally substituted with a group CONX<sub>1</sub>H or




and optionally a biuret compound containing an isocyanate group of general formula VI




said composition further comprising at least 1 weight % of at least one carbamate group and being free of dimerization catalyst selected from phosphine; aminopyridine, phosphoramidate, organometallic or tertiary amine.

67. (Previously Presented) A composition according to Claim 66, further comprising a compound of general formula VIII:




and/or a compound of general formula XIII:



wherein R'' represents H or a hydrocarbon group.


68. (Canceled)

69. (Currently Amended) A The compound of general formula III claim 70,  
wherein




in which

at least one of  $\text{NX}'_1\text{X}''_1$ ,  $\text{NX}'_2\text{X}''_2$  and  $\text{NX}'_3\text{X}''_3$  represents the group



in which  $\text{R}'$  is an aliphatic group and  $p$  is an integer ranging from 0 to 5, the others representing a group  $\text{NX}_1\text{H}$  with  $\text{X}_1$  representing a group  $\text{R}'-(\text{N}=\text{C}=\text{O})_p$  and  $\text{R}_2$  being a hydrocarbon group having 1 to 30 carbon atoms in which the hydrocarbon chain optionally is interrupted by one or more chalcogen atoms and optionally bears 1 to 3 OH groups, with the OH groups optionally substituted with a group  $\text{CONX}_1\text{H}$ , or






and


n is an integer ranging from 1 to 3.

70. (Currently Amended) A compound comprising at least 1.0 weight % carbamate groups, the compound formed according to of the formula III




in which:


the groups  $\text{NX}'_1\text{X}''_1$ ,  $\text{NX}'_2\text{X}''_2$  and  $\text{NX}'_3\text{X}''_3$  are selected from a group of general formula  $\text{NX}_1\text{H}$ , with  $\text{X}_1$  representing a group  $\text{R}'-(\text{N}=\text{C}=\text{O})_p$  in which  $\text{R}'$  is an aliphatic group and p is an integer from 0 to 5, or a group of general formula V,




or a uretidinedione group of formula IV,



or an isocyanurate group of formula XI:




or, a biuret group of formula XII:



wherein R'' represents H or a hydrocarbon group, R<sub>2</sub> being a hydrocarbon group having 1 to 30 carbon atoms in which the hydrocarbon chain optionally is interrupted by one or more chalcogen atoms and optionally bears 1 to 3 OH groups and n is an integer ranging from 1 to 3, wherein the optional OH groups in R<sub>2</sub> are optionally

substituted with a group selected from CONHX<sub>1</sub>, a group of formula VI, a group of formula IV, a group of formula XI or a group of formula XII, with the proviso that the compounds containing at least one group of formula NX<sub>1</sub>H, or CONX<sub>1</sub>H or group of formula V, also contain at least one group selected from a group of formula IV, group of formula XI, or group of formula XII, wherein formula VI is



71. (Previously Presented) A compound according to Claim 69, in which p is equal to 1 and containing 1, 2, 3 or 4 allophanate groups.

72. (Previously Presented) A compound according to Claim 69, wherein R' is an alkylene group ranging from 2 to 8 carbon atoms, optionally substituted with a hydrocarbon chain optionally bearing an isocyanate function, a norbornylmethylene group, a cyclohexylmethylene group or a 3,3,5-trimethylcyclohexyl methylene group.

73. (Previously Presented) A composition comprising:

- at least one composition according to Claim 66; and
- a polyol.

74. (Previously Presented) A composition comprising:

- at least one composition according to Claim 66; and
- an acrylate polyol which satisfies the following conditions for a dry extract:
  - Mw (weight-average molecular weight) not greater than 10,000; - Mn (number-average molecular weight) of not greater than 5000;
  - Mw/Mn (dispersity ratio) of not greater than 5;
  - number of OHs/molecule of greater than or equal to 2.

75. (Previously Presented) A composition comprising:

- at least one composition according to Claim 66; and
- a polyester polyol having a viscosity of not greater than 10,000 mPa.s at 25°C, and an Mw of between 250 and 8000.

76. (Previously Presented) A composition according to Claim 73, containing a crosslinking catalyst, which is optionally a latent catalyst.

77. (New) The process of claim 59, wherein the (poly)isocyanate composition comprises at least 1 weight % carbamate.